

PA6 - PA6.6

TIPO TYPE	Ø INTERNO INSIDE Ø	Ø ESTERNO OUTSIDE Ø	SCOPPIO (20°C) BURST (68°F)	ESERCIZIO (20°C) SERVICE (68°F)	RAGGIO MIN.CURV MIN. BEND RADIUS	PESI WEIGHTS	
PA6	(mm)	(mm)	(bar)	(bar)	(mm)	(gr/mt)	
TNPA60200X0400	2	4	167	56	25	11	
TNPA60250X0400	2,5	4	115	38	30	9	
TNPA60300X0500	3	5	125	42	30	14	
TNPA60300X0600	3	6	167	56	38	24	
TNPA60400X0600	4	6	100	33	45	18	
TNPA60500X0700	5	7	83	28	50	21	
TNPA60500X0800	5	8	115	38	62	35	
TNPA60600X0800	6	8	71	24	65	25	
TNPA60700X0900	7	9	63	21	70	28	
TNPA60600X1000	6	10	125	42	70	57	
TNPA60700X1000	7	10	88	29	75	45	
TNPA60800X1000	8	10	56	19	80	32	
TNPA60800X1200	8	12	100	33	80	71	
TNPA60900X1200	9	12	71	24	100	56	
TNPA61000X1200	10	12	45	15	100	39	
TNPA61000X1400	10	14	83	28	90	85	
TNPA61200X1400	12	14	38	13	100	46	
TNPA61200X1500	12	15	56	19	120	72	
TNPA61300X1500	13	15	36	12	150	50	
TNPA61400X1600	14	16	33	11	140	53	
TNPA61400X1800	14	18	63	21	150	114	
TNPA61600X1800	16	18	29	10	410	60	
PRESSURE REDUCTION FACTOR TO THE INCREMENT OF THE TEMPERATURE							
-40°C	0°C	+30°C	+40°C	+60°C	+80°C	+110°C	+130°C
1	1	0,83	0,71	0,54	0,48	0,36	0,30

TIPO TYPE	Ø INTERNO INSIDE Ø	Ø ESTERNO OUTSIDE Ø	SCOPPIO (20°C) BURST (68°F)	ESERCIZIO (20°C) SERVICE (68°F)	RAGGIO MIN.CURV MIN. BEND RADIUS	PESI WEIGHTS
PA6.6	(mm)	(mm)	(bar)	(bar)	(mm)	(gr/mt)
TNPA 660200X0400	2	4	300	100	25	11
TNPA 660250X0400	2,5	4	208	69	30	9
TNPA 660300X0500	4	6	180	60	40	18
TNPA 660400X0500	6	8	129	43	60	25
TNPA 660300X0600	8	10	100	33	70	32
PRESSURE REDUCTION FACTOR TO THE INCREMENT OF THE TEMPERATURE						
	0°C	+30°C	+40°C	+60°C	+80°C	
	1	0,83	0,71	0,54	0,48	